

Analysis Report 18.06134.03 Date 06-12-2018 Page 1/4



Your notice of 25-10-2018

Your reference

Date 06-12-2018

Analysis Report 18.06134.03

Required tests:

EN 13773 (2003)

Identification number	Information given by the client	Date of receipt
T1824747	Admiral backdrop, 320 g/m ²	25-10-2018

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference:

T1824747 - Admiral backdrop, 320 g/m²

<u>Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.</u>

Date of ending the test

12-11-2018

Standard used

EN 1101 (1995) + A1 (2005)

Product standard

EN 13773 (2003)

Deviation from the standard

-

Conditioning

20°C, relative humidity 65%

Ignition

Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

Flame application	Cases of	Cases of
time (s)	ignition	non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated No ignition within $20\ \mathrm{s}$



Width

7714411		
Flame application	Cases of	Cases of
time (s)	ignition	non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated No ignition within 20 $\ensuremath{\mathrm{s}}$



Reference:

T1824747 - Admiral backdrop, 320 g/m²

<u>Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.</u>

Date of ending the test

19-11-2018

Standard used

EN 13772 (2011)

Product standard

EN 13773 (2003)

Deviation from the standard

_

Conditioning

20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face B	Face B
Severance1st thread	no	yes	yes	
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	195	210	205	200
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face B	Face B
Severance1st thread	yes	yes	yes	yes
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	190	200	190	195
Flaming debris	no	no	no	no

Classification in accordance with EN

Class 2

13773